



Thermal Transfer Ribbons

US150

Wax
Resin

Flat Head

US150 is our ultra-premium flat head wax/resin ribbon, designed to provide a high-resolution image on to a wide variety of label stocks. It has an excellent smear, scratch resistance and a good chemical resistance.

RIBBON SPECIFICATION

RIBBON

GRADE : WAX/RESIN, FLAT-HEAD
COLOUR : BLACK
THICKNESS : 10.0±0.3 µm
Anti-static formulation ink
BASE FILM : POLYESTER (4.5±0.3 µm)
BACK COAT : SILICONE BASED
INK MELTING POINT : 75 °C

STORAGE AND USE

STORAGE : 0-40 °C (32-104 °F), 20-80 %RH
USE : 5-35 °C (41-95 °F), 20-80 %RH

RECOMMENDED LABEL STOCK

Coated paper, Glossy paper, Synthetic paper, PET

CERTIFICATIONS

HEAVY METALS : 2011/65/EU, (EU)2015/863 (RoHS, RoHS2.0)
REACH : SVHC free
HALOGEN-FREE : IEC 61249-2-21
ISEGA CERTIFIED : Regulation (EC) no.1935/2004
FDA, BPA

*Above documents are available upon request.

APPLICATION




BARCODE



RIBBON PERFORMANCE

IMAGE DENSITY (KONICA MINOLTA FD-5)




SCRATCH /SMUDGE RESISTANCE (ANSI)



Pressure: 1.96x10⁴ Pa

Stroke Cycle: 500 cycles with corrugated paper

PRINT SPEED (mm/sec)



UV RESISTANCE (%)



168 hours exposed on UV test machine.

TRANSFER SENSITIVITY



SOLVENT RESISTANCE



* The numerical value indicated on this sheet is catalog value, and is not guarantee value.

* The information shown above is tentative and subject to change without notice.



UNION CHEMICAL Global Network

Japan : Union Chemicar Co., Ltd.

China (Shanghai) : Union Chemicar (Shanghai) Co., Ltd.

China (Tianjin) : Union Chemicar (Tianjin) Co., Ltd.

United States : Union Chemicar America Inc.

United Kingdom : Union Chemicar UK Limited

Netherlands : Union Chemicar Europe B.V.

Germany : Union Chemicar Deutschland GmbH

India : Union Chemicar India Pvt. Ltd.



ISO 9001
JQA-1784

[26 Jun. 2023]